

Please amend the paragraph beginning on line 23 of page 5 as follows:

In a third embodiment of the present invention, a filter laminate is provided including a plurality of ~~disereet~~ discrete layers of material, each layer being adjacent at least one other layer, including at least a first asymmetric membrane as a layer, and a second membrane as a distinct layer, the laminate including a bond between each of the adjacent layers, wherein the bond is formed after the formation of the material of the layers.

STW
10/8/10
Please amend the paragraph beginning on line ²⁹28 of page 5 as follows:

In a fourth embodiment of the present invention, a method of making a filter laminate is provided, including the steps of providing a first plurality of ~~disereet~~ discrete layers of material; contacting the layers to form a first stack, wherein each layer is adjacent at least one other layer in the stack; forming a bond between adjacent layers in the first stack, wherein the bond is formed after the formation of the material of the layers, thereby forming a first laminated stack layer; contacting the first laminated stack with a second layer of material; and forming a bond between the first laminated stack layer and the second layer, wherein the bond is formed after the formation of the material of the layers, thereby forming a filter laminate.

STW
10/8/10
Please amend the paragraph beginning on line ⁷6 of page 6 as follows:

In another aspect, the second layer includes a plurality of ~~disereet~~ discrete layers, wherein at least one of the ~~disereet~~ discrete layers includes an asymmetric membrane.

STW
10/8/10
Please amend the paragraph beginning on line ²¹20 of page 6 as follows:

In a fifth embodiment of the present invention, a method of making a filter laminate is provided including the steps of providing a plurality of ~~disereet~~ discrete layers of material, wherein at least one layer is an asymmetric membrane and at least one layer is a hot melt

10603425

Appl. No. : 10/603,425
Filed : June 24, 2003

adhesive; contacting each layer with at least one other layer to form a stack including at least two layers; and forming a bond between adjacent layers, wherein the bond is formed after the formation of the material of the layers, thereby forming a filter laminate.

JTW
10/8/10

Please amend the paragraph beginning on line ²⁸27 of page 6 as follows:

In a sixth embodiment of the present invention, a method of making a filter laminate is provided including the steps of providing a plurality of ~~disereet~~ discrete layers of material, wherein at least one layer is an asymmetric membrane including polyvinylidene fluorides, polyamides, or cellulosic derivatives; contacting each layer with at least one other layer to form a stack including at least two layers; and forming a bond between adjacent layers, wherein the bond is formed after the formation of the material of the layers, thereby forming a filter laminate.

JTW
10/8/10

Please amend the paragraph beginning on line ⁴3 of page 7 as follows:

In a seventh embodiment of the present invention, a method of making a filter laminate is provided including the steps of providing a plurality of ~~disereet~~ discrete layers of material, wherein at least one layer is an asymmetric membrane and wherein at least one layer including polypropylene, polyolefin, polyethylene, nylon, paper, cellulose, glass fiber, or acrylic; contacting each layer with at least one other layer to form a stack including at least two layers; and forming a bond between adjacent layers, wherein the bond is formed after the formation of the material of the layers, thereby forming a filter laminate.

JTW
10/8/10

Please amend the paragraph beginning on line ¹²11 of page 7 as follows:

In an eighth embodiment of the present invention, a method of making a filter laminate is provided including the steps of providing a plurality of ~~disereet~~ discrete layers of material, wherein at least one layer is an asymmetric membrane and wherein at least one additional layer is a membrane; contacting each layer with at least one other layer to form a stack including at least

10603425

Appl. No. : 10/603,425
Filed : June 24, 2003

two layers; and forming a bond between adjacent layers, wherein the bond is formed after the formation of the material of the layers, thereby forming a filter laminate.

JTW
10/8/10

Please amend the paragraph beginning on line ¹⁹18 of page 7 as follows:

In a ninth aspect of the present invention, a method for filtering ink is provided, the method including providing a filter laminate, the filter laminate including a plurality of ~~disereet~~ discrete layers of material, each layer being adjacent at least one other layer, wherein at least one layer is an asymmetric membrane, the laminate including a bond between each of the adjacent layers, wherein the bond is formed after the formation of the material of the layers; and passing an ink through the filter laminate, whereby the ink is filtered.

JTW
10/8/10

Please amend the paragraph beginning on line ²⁷19 of page 12 as follows:

The invention thus provides a filter laminate, with multiple ~~disereet~~ discrete layers of material, with each layer being adjacent and bonded to least one other layer. At least one of the layers is an asymmetric membrane. In contrast to laminates that have a membrane cast onto a support layer, in the present invention the bond between the layers is formed after the formation of the material of the layers. In a preferred embodiment, the asymmetric membrane is a highly asymmetric ultrafilter or microfilter. The average diameter of the large pores on the dull or open side of the membrane is at least about 5 times larger, preferably between 10 and 20,000 times larger, than the average diameter of the pores on the skin or shiny side of the membrane. The asymmetric membranes may be gradually asymmetric, wherein the flow channels between the skin surface and the opposite surface generally increase gradually in size. As an alternative, the membranes may have a mixed isotropic and anisotropic structure, wherein the support structure of the membrane, between the two surfaces thereof, has a region with flow channels of relatively constant diameter. This region typically adjoins a region of flow channels with gradually increasing or decreasing diameters.

Please amend the Abstract on page 41 as follows: